

DIP-DYABLE POLYCARBONATE PROCESS

5

FIELD OF THE INVENTION

The present invention relates to plastic articles and more particularly to colored articles, and to a process for their preparation.

10

SUMMARY OF THE INVENTION

A process for tinting of articles molded from a polymeric resin is disclosed. Preferably, the article is molded from polycarbonate and the process entails immersing the molded article in a dye bath that contains water, dye, a carrier and an optional surfactant. The carrier is a compound conforming to

15



wherein R^1 and R^2 independently denote H or C_{1-18} alkyl, benzyl, benzoyl or phenyl radical which may be substituted in the aromatic ring by alkyl and or halogen, preferably R^1 =butyl, R^2 =H, n is 2 or 3 and m is 2 to 35. The method is especially useful in the manufacture of tinted lenses.

20

BACKGROUND OF THE INVENTION

Articles molded of polycarbonate are well known. The utility and method for making colored articles that are prepared from pigmented polycarbonate compositions are well known. Also known are processes for dyeing articles molded of resins, including polycarbonates, and including lenses that have been tinted by immersion in special pigmenting mixtures. Among the advantages attained by such tinting of lenses, mention has been made of reduced light transmission and mitigation of glare.

25

30

U.S. patent 4,076,496 disclosed a dye bath composition suitable for dyeing hard-coated polarized lenses; the composition of the bath included


"Express Mail" mailing label number ET700177090US

Date of Deposit November 7, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)



Signature of person mailing paper or fee)

10040178-110701

a dye and as a solvent, a mixture of glycerol and ethylene glycol, optionally with a minor proportion of water or other organic solvent.

U.S. Patent 5,453,100 disclosed polycarbonate materials that are
5 dyed by immersion into a mixture of dye or pigment dissolved in a solvent
blend. The blend is made up of an impregnating solvent that attacks the
polycarbonate and allows the impregnation of the dye or pigment and a
moderating solvent that mitigates the attack of the impregnating solvent.
The impregnating solvent thus disclosed includes at least one solvent
10 selected from dipropylene glycol monomethyl ether, tripropylene glycol
monomethyl ether and propylene glycol monomethyl ether.
PCT/CA99/00803 (WO 0014325) disclosed tinting plastic articles by
immersion in an aqueous dispersion and exposing the dispersion and
immersed article to microwave radiation. JP 53035831 B4 disclosed
15 polycarbonate moldings that are dyed in aqueous dispersion containing
dispersed dyes and diallyl phthalate, o-phenylphenol or benzylalcohol.
Also, JP 55017156 disclosed aliphatic polycarbonate lenses that are
colored with a liquor containing dyes and water. JP 56031085 (JP-104863)
disclosed compositions containing a disperse dye in an aliphatic ketone
20 and polyhydric alcohol said to be useful in coloring polycarbonate films at
room temperature. JP2000248476 disclosed a molded polycarbonate bolt
that was dyed with a solution containing dyes, an anionic leveling agent
and then treated with a solution containing thiourea dioxide.

25 U.S. patent 4,812,142 disclosed polycarbonate articles dyed at a
temperature of 200°F or above in a dye solvent having a boiling point of at
least 350 °F, and U.S. Patent 3,514,246 disclosed immersing molded
polycarbonate articles in an emulsified dye liquor which contains a water
insoluble dyestuff, an oil-soluble surface active agent dissolved in an
30 aliphatic hydrocarbon solvent and water. The procedure was repeated with
similar results where the surfactant was replaced by a poly(oxyethylene)
derivative. U.S. Patent 3,532,454 disclosed dyeing of polycarbonate fibers

10040178-110701

with a dye composition that contains at least one of alkoxyalkylbenzyl ether, alkylene glycol di-benzyl ether, benzoic acid alkoxyalkyl ester or phenoxy acetic acid-alkoxyalkyl ester. U.S. Patent 3,630,664 disclosed a dye bath that required the presence of a carbonate conforming to a
5 specific formula, e.g. ethyl-benzyl-carbonate.

DETAILED DESCRIPTION OF THE INVENTION

The inventive method and the dye bath composition of this invention are useful for dyeing plastic articles molded of a variety of
10 resinous molding compositions. The suitable resins include both thermoplastic and thermosetting compositions. Among the suitable resins, mention may be made of (co)polyesters, (co)polycarbonates (including aromatic and aliphatic polycarbonate such as allyldiglycol carbonate e.g., trade name CR-39), polyesterpolycarbonate copolymers, styrenic
15 copolymers such as SAN and acrylonitrile-butadiene-styrene (ABS), acrylic polymers such as polymethylmethacrylate and ASA, polyamide, and polyurethane and blends of one or more of these resins. Particularly, the invention is applicable to polycarbonates, and most particularly to thermoplastic aromatic polycarbonates.

20 The molding compositions useful in molding the articles that are suitable for use in the inventive process may include any of the additives that are known in the art for their function in these compositions and include at least one of mold release agents, fillers, reinforcing agents in
25 the form of fibers or flakes most notably metal flakes such as aluminum flakes, flame retardant agents, pigments and opacifying agents such as titanium dioxide and the like, light-diffusing agents such as polytetrafluoroethylene, zinc oxide, Paraloid EXL-5136 available from Rohm and Haas and crosslinked polymethylmethacrylate minispheres
30 (such as n-licrospheres from Nagase America) UV-stabilizers, hydrolytic stabilizers and thermal stabilizers.

Articles to be dyed in accordance with the inventive process may be molded conventionally by methods that have long been practiced in the plastics arts and include articles molded by compression molding, injection molding, rotational molding, extrusion, injection and extrusion blow

5 molding, and casting, the method of molding the articles is not critical to the practice of the inventive process. The molded articles may be any of a vast variety of useful items and include computer face-plates, keyboards, bezels and cellular phones, color coded packaging and containers of all types, including ones for industrial components, residential and
10 commercial lighting fixtures and components therefor, such as sheets, used in building and in construction, tableware, including plates, cups and eating utensils, small appliances and their components, optical and sun-wear lenses, as well as decorative films including such films that are intended for use in film insert molding.

15

Polymer resins particularly suitable in the present context include one or a mixture of two or more resins selected from the group consisting of polyester, polycarbonate, polyesterpolycarbonate copolymer, acrylonitrile-butadiene-styrene (ABS), polyamide, polyurethane,
20 polymethylmethacrylate and styrenic copolymer. While styrenic copolymers, most notable styrene-acrylonitrile copolymers are thus suitable, the inventive process is not applicable for tinting of homopolystyrene.

25

According to the present invention, the molded article to be tinted, preferably a lens, is immersed in the dyeing bath mixture for a time and at temperature sufficient to facilitate at least some impregnation, or diffusion, of the dye into the bulk of article thus effecting tinting thereof. For tinting articles made of aromatic polycarbonate the immersion may be carried out
30 at a temperature of about 90 to 99°C and the immersion time is typically less than 1 hour, most preferably in the range of 1 to 15 minutes.

However, due to the efficiency of dye up-take, thermoplastic resins that

10040178-110701
T0201T "B T04001

have low heat distortion temperature may be dyed at lower temperatures than polycarbonate. For example, polyurethanes, SAN and polyamide may be readily dyed using the solution composition that is typically used for tinting polycarbonate, heated to only about 60°C, 90°C and 105°C, respectively. The tinted article is then withdrawn at a desired rate, including a rate sufficient to effect a tinting gradient, the portion of the article that remains in the mixture longest is impregnated with the most dye so that it exhibits the darkest color tint.

10 The dyeing bath mixture contains

- (a) water in an amount of 94 to 96 pbw (percent by weight relative to the weight of the dyeing bath mixture)
 - (b) an amount of dye sufficient to effect tinting, generally 0.1 to 15 pbw, preferably 0.3 to 0.5 pbw
 - (c) a carrier conforming to formula (i) in an amount of 1 to 2 pbw
- (i) $R^1 [-O-(CH_2)_n]_m OR^2$

wherein R^1 and R^2 independently one of the other denote H or C_{1-18} alkyl, benzyl, benzoyl or phenyl radical which may be substituted in the aromatic ring by alkyl and or halogen, n is 2 or 3 and m denoted 2 to 35. In a preferred embodiment R^1 denotes butyl and R^2 denotes H, and optionally

- (d) a surfactant in an amount of 3 to 4 pbw.

25

The dyes to be used in accordance with the invention are conventional and include fabric dyes and disperse dyes as well as dyes that are known in the art as suitable for tinting of polycarbonates. Examples of suitable disperse dyes include Disperse Blue #3, Disperse Blue #14, Disperse Yellow #3, Disperse Red #13 and Disperse Red #17. The classification and designation of the dyes recited in this specification are in accordance with "The Colour Index", 3rd edition published jointly by

the Society of Dyes and Colors and the American Association of Textile Chemists and Colorists (1971), incorporated herein by reference.

Dyestuffs can generally be used either as a sole dye constituent or as a component of a dye mixture depending upon the color desired. Thus, the

5 term dye as used herein includes dye mixture.

The dye class known as "Solvent Dyes" is useful in the practice of the present invention. This dye class includes the preferred dyes Solvent Blue 35, Solvent Green 3 and Acridine Orange Base. However Solvent
10 Dyes, in general, do not color as intensely as do Disperse Dyes.


Among the suitable dyes special mention is made of water-insoluble azo, diphenylamine and anthraquinone compounds. Especially suitable are acetate dyes, dispersed acetate dyes, dispersion dyes and dispersol
15 dyes such as are disclosed in Colour Index, 3rd edition, vol. 2, The Society of Dyers and Colourists, 1971, pp. 2479 and pp. 2187-2743, respectively all incorporated herein by reference. The preferred dispersed dyes include Dystar's Palanil Blue E-R150 (anthraquinone/Disperse Blue) and DIANIX Orange E-3RN (azo dye/ CI Disperse Orange 25). Note that phenol red
20 and 4-phenylazophenol do not dye polycarbonate in accordance with the inventive process.

The dyes known as "direct dyes" and the ones termed "acid dyes" are not suitable in the practice of the invention for polycarbonate.
25 However acid dyes are effective with nylon.

The amount of dye used in the mixture can vary; however, only small amounts are typically needed to sufficiently tint an article in accordance with the invention. A typical dye concentration in the bath is
30 0.4 pbw, but there is considerable latitude in this regard. Generally, dyes may be present in the solvent mixture at a level of about 0.1 to 15 pbw preferably 0.3 to 0.5 pbw. Where a dye mixture is used and the rates of consumption of the individual components differ one from the others, dye

components will have to be added to the bath in such a manner that their proportions in the bath remain substantially constant.

The carrier suitable in the context of the invention conforms
5 structurally to



wherein R^2 and R^1 independently one of the other denotes H, C_{1-18} alkyl, benzyl, benzoyl or phenyl radical which may be substituted in the aromatic
10 ring by alkyl and or halogen, n is 2 or 3 and m is 2-35, preferably 2 to 12, most preferably 2. Most preferably R^2 denotes butyl and R^1 denotes H.

The optional surfactant (emulsifier) may be used in an amount of 0
to 15 pbw, preferably 0.5 to 5 pbw, most preferably 3 to 4 pbw.

15 The emulsifier suitable in the context of the invention is a substance that holds two or more immiscible liquids or solids in suspension (e.g., water and the carrier). Proper emulsification is essential to the satisfactory performance of a carrier. An emulsified carrier readily disperses when
20 poured into water, and forms a milky emulsion upon agitation. Emulsifiers which may be used include ionic, non-ionic, or mixtures thereof. Typical ionic emulsifiers are anionic, including amine salts or alkali salts of carboxylic, sulfamic or phosphoric acids, for example sodium lauryl sulfate, ammonium lauryl sulfate, lignosulfonic acid salts, ethylene diamine
25 tetra acetic acid (EDTA) sodium salts and acid salts of amines such as laurylamine hydrochloride or poly(oxy-1,2-ethanediyl), alpha.-sulfo-omega-hydroxy ether with phenol 1-(methylphenyl)ethyl derivative ammonium salts; or amphoteric, that is, compounds bearing both anionic and cationic groups, for example lauryl sulfobetaine; dihydroxy ethylalkyl betaine;
30 amido betaine based on coconut acids; disodium N-lauryl amino propionate; or the sodium salts of dicarboxylic acid coconut derivatives. Typical non-ionic emulsifiers include ethoxylated or propoxylated alkyl or

aryl phenolic compounds such as octylphenoxypolyethyleneoxyethanol or poly(oxy-1,2-ethanediyl),alpha-phenyl-omega-hydroxy, styrenated. The preferred emulsifier is a mixture of C₁₄-C₁₈ and C₁₆-C₁₈ ethoxylated unsaturated fatty acids and poly(oxy-1,2-ethanediyl), alpha-sulfo-omega-hydroxy ether with phenol 1-(methylphenyl) ethyl derivative ammonium salts and poly(oxy-1,2-ethanediyl),alpha-phenyl-omega-hydroxy, styrenated.

Emulsifiers, such as disclosed in "Lens Prep II", a commercial product of Brain Power International (BPI) are also useful for practicing the present invention. LEVEGAL DLP a product of Bayer Corporation is a pre-formulated mixture of a suitable carrier (polyglycol ether) with emulsifiers that are useful together with a dye and water for preparing a dyeing bath suitable for molded parts, preferably polycarbonate parts.

It has been noted above that by eliminating emulsifiers from the dyeing mixture special color effects may be produced. For example, the use of IGEPAL CA-210 in the dye mixture without the emulsifier results in a polycarbonate article having a special marbling effect. This technique is also an excellent way to produce camouflage colors.

According to an embodiment of the present invention, an article molded of the resins suitable in accordance with the invention, preferably molded of a polycarbonate composition, is immersed in the inventive dyeing bath. To reduce processing time, while keeping evaporation losses to a minimum, some dyeing baths may be heated to temperatures below 100°C, preferably below 96°C. In the course of dyeing in accordance with the present invention, it is preferred that the dyeing bath is at a temperature below that at which the bath is at the state of ebullition. The optimum temperature of the bath is to some degree influenced by the molecular weight of the polycarbonate, its additives and the chemical nature of the dye.

In a preferred embodiment in the tinting of parts made of polycarbonate, a dye that is known to be suitable for compounding with polycarbonate composition is mixed with a carrier and water and optional surfactant to form a dye-bath mixture. In accordance with this

- 5 embodiment of the invention, the article is immersed in the dyeing bath and withdrawn after only a few minutes to provide a color-tinted product. The length of time in which the article should remain immersed in the bath and the process conditions depends upon the desired degree of tint.

- 10 Naturally, higher concentrations of dye and higher temperatures will increase the rate of dyeing.

- In order to impart a graded tint, the molded article may be immersed in the dyeing bath and then slowly withdrawn therefrom. A
15 graded tint results because the portion of the article that remains in the mixture longest is impregnated with the most dye.

- The present invention may be more fully understood with reference to the examples set forth below. The examples are in no way to be
20 considered as limiting, but instead are provided as illustrative of the invention.

1004018-110701

EXAMPLES

Example 1

5 The process was demonstrated in reference to an article molded of polycarbonate. Dye (0.4 pbw) was mixed with 6.6 pbw LEVEGAL, and then 93 pbw water were added. The mixture was then heated to 95° C and the article was then dipped. (Note that the order of dye and LEVEGAL addition to the mixture must be followed for best results. If this order is not followed, the parts will not absorb dyes efficiently.) This is probably due to
10 the need to have the dye "wetted" by the emulsifier. "Wetting" in this context refers to the use of a surface active agent which, when added to water, causes the water to penetrate more easily into, or to spread over the surface of another material by reducing the surface tension of the water.

15 Appreciable dyeing was achieved after 1-15 minutes, depending on the selected color and color density. The part was removed from the mix, rinsed with copious quantities of water to remove any traces of excess dye and dried. The exposure time, dye concentration and mix temperature,
20 may be adjusted to yield colors of the desired shades and density. The table below summarizes the results of several experiments that were carried out in accordance with the present invention. The article tinted in accordance with these experiments was molded of polycarbonate, Makrolon 3107 a homopolycarbonate based on bisphenol A having a MFR
25 of 5-7.5 g/10 min. (in accordance with ASTM D 1238) a product of Bayer Corporation. "Time " denotes the time of residence (in minutes) of the article in the dyeing bath. Light transmission (%) and haze (%) were determined in accordance with ASTM D 1003.

TABLE 1

DYE	TIME	LIGHT TRANSMISSION	HAZE
Polycarbonate (control)		90.4	0.9
Acridine Orange	10	90.4	1.1
Acridine Orange Base	3	75.5	9.5
Basic Blue 3	10	90.3	7.2
Methyl Violet	10	64.4	1.4
Quinoline Yellow	10	89.7	1.0
Sudan III	10	55.8	1.8
Flourescein	10	89.7	1.0
Red G (granular)	10	32.7	2.5
Red 5B (granular)	10	67.8	2.2
Disperse Yellow 201	10	84.2	3.2
Solvent Green 3	10	69.8	1.4
Solvent Green 3	3	85.0	1.3
Disperse Orange 47	10	57.3	1.8
Disperse Violet 26	10	20.6	3.0
Palanil Blue	10	16.6	2.6
Solvent Blue 25	3	27.8	4.1
Disperse Orange 25	3	55.2	4.0

5

Example 2

Dip-dyed articles molded from ABS (Lustran LGM from Bayer Corporation) and from a blend of polycarbonate/ABS (Bayblend FR 110 from Bayer Corporation) have been prepared in accordance with the inventive process. These articles molded from both natural resins and resins containing an amount of titanium dioxide sufficient to render the articles opaque were dyed in a bath as described in Example 1. The articles were dip-dyed to a uniform color.

10

Articles molded of polycarbonate (Makrolon 3107 from Bayer Corporation) and containing sufficient amount of titanium dioxide to make the articles either translucent or opaque were also prepared in accordance with the inventive process. The articles were dip-dyed to a uniform color in a bath as described in Example 1.

Example 3

Dye, 0.4pbw, was mixed with 6.6 pbw of a carrier, 3 pbw BPI Lens Prep II, and then 93 pbw water to form a dyeing bath. The bath was then heated to 95° C and a part molded of polycarbonate was dipped in the dyeing bath. The part was removed from the mix, rinsed with copious quantities of water to remove any traces of excess dye and dried. The immersion time (in minutes), optical properties and the respective carrier used in carrying out these runs are summarized in table 2.

TABLE 2

DYE	TIME	LIGHT TRANSMISSION	HAZE	CARRIER
Polycarbonate (control)		90.4	0.9	
Disperse Orange 25	3	55.0	9.2	Igepal
Disperse Orange 25	3	78.0	1.3	Tergitol
Disperse Orange 25	3	90.5	1.6	Triton X-405
Palanil Blue	5	67.3	1.1	Brij 30

IGEPAL CA-210 refers to polyoxyethylene (2) isooctylphenyl ether $[4-(C_8H_{17})C_6H_4(OCH_2CH_2)_nOH, n=2]$

TERGITOL NP-9 refers to nonylphenol polyethylene glycol ether $[C_9H_{19}C_6H_4(OCH_2CH_2)_nOH, n=9]$

TRITON X-405 refers to polyoxyethylene (40) isooctylphenyl ether $[4-(C_8H_{17})C_6H_4(OCH_2CH_2)_nOH, n=40]$

BRIJ 30 refers to polyoxyethylene (4) lauryl ether $[C_{12}H_{25}(OCH_2CH_2)_nOH, n=4]$

Although the present invention has been described in connection with preferred embodiments, it will be appreciated by those skilled in the art that additions, modifications, substitutions and deletions not specifically described may be made without departing from the spirit and scope of the invention defined in the appended claims.

5

10040178-110701